#### **CLAIMS**

1. A method comprising:

5

20

- (i) applying a photopatternable silicone composition to a surface of a substrate;
- (ii) exposing a portion of the film to radiation to produce a partially exposed film having non-exposed regions covering at least a portion of the surface and exposed regions covering the remainder of the surface;
- (iii) heating the partially exposed film for an amount of time such that the exposed regions are substantially insoluble in a developing solvent and the non-exposed regions are soluble in the developing solvent;
- (iv) removing the non-exposed regions of the heated film with the developing solvent to form a patterned film;
  - (v) heating the patterned film; and
  - (vi) removing all or a portion of the product of step (v).
- 15 2. A method comprising:
  - (i) applying a photopatternable silicone composition to a surface of a substrate;
  - (ii) exposing a portion of the film to radiation to produce a partially exposed film having non-exposed regions covering at least a portion of the surface and exposed regions covering the remainder of the surface;
  - (iii) heating the partially exposed film for an amount of time such that the exposed regions are substantially insoluble in a developing solvent and the non-exposed regions are soluble in the developing solvent;
    - (iv) removing the non-exposed regions of the heated film with the developing solvent to form a patterned film;
- 25 (v) removing all or a portion of the patterned film.
  - 3. The method of claim 1 or claim 2, where the substrate is an active surface of a semiconductor wafer.
- 4. The method of claim 1 or claim 2, where the photopatternable silicone composition comprises:
  - (A) an organopolysiloxane containing an average of at least two silicon-

bonded alkenyl groups per molecule,

5

15

- (B) an organosilicon compound containing an average of at least two silicon-bonded hydrogen atoms per molecule in a concentration sufficient to cure the composition, and
- (C) a catalytic amount of a photoactivated hydrosilylation catalyst.
- 5. The method of claim 1 or claim 2, where the removing step is carried out using an etching solution comprising an organic solvent and a base.
- 10 . 6. The method of claim 5, where the etching solution contains no more than 25% water based on the weight of the etching solution.
  - 7. The method of claim 5, where the organic solvent is selected from a monohydric alcohol, a dihydric alcohol, a monoether, a diether, a polar aprotic solvent, and combinations thereof.
  - 8. The method of claim 5, where the base is selected from ammonium hydroxide, cesium hydroxide, potassium hydroxide, sodium hydroxide, and combinations thereof.
- 9. The method of claim 5, where the base is selected from phosphazene, tetraalkyl
  ammonium hydroxides, and combinations thereof.
  - 10. Use of the method of claim 1 or claim 2 for rework, photoresist, or cleaning applications.

WO 2005/017627 PCT/US2003/023601

## **AMANDED CLAIMS**

[received by the International Bureau on 27 April 2004 (27.04.04); original claims 1-10 replaced by amended claims 1-10 (2 pages)]

### 1. A method comprising:

- (i) applying a photopatternable silicone composition to a surface of a substrate to form a film, where the photopatternable silicone composition comprises
- (A) an organopolysiloxane containing an average of at least two silicon-bonded alkenyl groups per molecule,
- (B) an organosilicon compound containing an average of at least two silicon-bonded hydrogen atoms per molecule in a concentration sufficient to cure the composition, and
  - (C) a catalytic amount of a photoactivated hydrosilylation catalyst;
- (ii) exposing a portion of the film to radiation to produce a partially exposed film having non-exposed regions covering at least a portion of the surface and exposed regions covering the remainder of the surface;
- (iii) heating the partially exposed film for an amount of time such that the exposed regions are substantially insoluble in a developing solvent and the non-exposed regions are soluble in the developing solvent;
- (iv) removing the non-exposed regions of the heated film with the developing solvent to form a patterned film;
  - (v) heating the patterned film; and
  - (vi) removing all or a portion of the product of step (v).

20

25

5

10

15

#### 2. A method comprising:

- (i) applying a photopatternable silicone composition to a surface of a substrate to form a film, where the photopatternable silicone composition comprises
- (A) an organopolysiloxane containing an average of at least two silicon-bonded alkenyl groups per molecule,
- (B) an organosilicon compound containing an average of at least two silicon-bonded hydrogen atoms per molecule in a concentration sufficient to cure the composition, and
  - (C) a catalytic amount of a photoactivated hydrosilylation catalyst;
- (ii) exposing a portion of the film to radiation to produce a partially exposed film having
   non-exposed regions covering at least a portion of the surface and exposed regions covering the remainder of the surface;

WO 2005/017627 PCT/US2003/023601

19

- (iii) heating the partially exposed film for an amount of time such that the exposed regions are substantially insoluble in a developing solvent and the non-exposed regions are soluble in the developing solvent;
- (iv) removing the non-exposed regions of the heated film with the developing solvent toform a patterned film;
  - (v) removing all or a portion of the patterned film.
  - 3. The method of claim 1 or claim 2, where the substrate is an active surface of a semiconductor wafer.

10

- 4. The method of claim 1 or claim 2, where the removing step is carried out using an etching solution comprising an organic solvent and a base.
- 5. The method of claim 4, where the etching solution contains no more than 25% water based on the weight of the etching solution.
  - 6. The method of claim 4, where the organic solvent is selected from a monohydric alcohol, a dihydric alcohol, a monoether, a diether, a polar aprotic solvent, and combinations thereof.
- 7. The method of claim 4, where the base is selected from ammonium hydroxide, cesium hydroxide, potassium hydroxide, sodium hydroxide, and combinations thereof.
  - 8. The method of claim 4, where the base is selected from phosphazene, tetraalkyl ammonium hydroxides, and combinations thereof.

25

30

- 9. The method of claim 1 or claim 2, where the removing step is carried out using an etching solution comprising: a) tetramethylammonium hydroxide pentahydrate and isopropyl alcohol; b) cesium hydroxide, water, and isopropyl alcohol; c) potassium hydroxide and isopropyl alcohol; d) tetramethylammonium hydroxide pentahydrate, water, and isopropyl alcohol; or e) tetramethylammonium hydroxide pentahydrate and 1-methoxy-2-propanol.
- 10. Use of the method of claim 1 or claim 2 for rework, photoresist, or cleaning applications.

# **AMENDED SHEET (ARTICLE 19)**